



LEADERS IN CORROSION PREVENTION AND SEALING TECHNOLOGY

TECHNICAL DATA SHEET

OVER 130 YEARS SERVICE TO INDUSTRY



Densopol 60HT

anti-corrosion tape designed for tropical climates.

Composition

Synthetic fibre fabric impregnated and coated with polymer modified bitumen compound laminated to PVC sheeting. The compound surface is protected by a plastic film interleaving which is discarded during application.

Uses

Densopol 60HT is used for the protection and refurbishment of steel and ductile pipes, joints, tie rods, bends and fittings in tropical climates.

Characteristics

Densopol 60HT is:

- exceptionally resistant to shear,
- resistant to damage by backfill, and
- suitable for tropical climates.

Primer

Denso Primer D

Typical Properties

Colour	Black	
Backing thickness	85 µ	ASTM D1000
Total thickness	1.5 mm	ASTM D1000
Weight	1.7 kg/m ²	
Elongation	22%	ASTM D1000
Tear Strength	30N	ASTM D1004
Insulation resistance	10 ⁶ MΩ	ASTM D257
Dielectric strength	>20 kV/layer	
Impact resistance	5 Nm	ASTM G14
Adhesion (180° peel)	to primed steel	3.0 N/mm
	to self	2.5 N/mm

Application

see *Instructions for Use* for additional detail

Application temperature: 15°C to 50°C

Testing

Ensure the application has:

- sufficient tension,
- no creases or folds, and
- sufficient overlap.

Availability

Densopol 60 HT is available in 10 or 30 metre rolls in widths from 50 mm to 300 mm.

Additional sizes may be available on request.

Storage conditions

Store in a cool dry place in original packaging

Important: Winn & Coales (Denso) Ltd pursue a policy to develop and continually improve all of our products and therefore the information given in this data sheet is intended as a general guide and does not constitute a warranty of specification. However, our sales personnel are committed to assist the user in establishing the suitability of the product for its intended purpose and additional specific information is available on request. Winn & Coales (Denso) Ltd operate a Quality Management System registered to BS EN ISO 9001 (BSI Certificate no. FM01548) and an Environmental Management System registered to BS EN 14001 (BSI Certificate 583748).

Revision date: 18/08/2016

Winn & Coales (Denso) Ltd
Denso House, Chapel Road,
London SE27 0TR, United Kingdom



Tel: +44 (0) 20 8670 7511
Fax: +44 (0) 20 8761 2456
Email: mail@denso.net Web: www.denso.net